



**RAWSON MATERIALS
EXCLUSIVELY DISTRIBUTES
TO
ASTRO AGGREGATES**



ASTRO
AGGREGATES

REFERENCE TABLE

NEW YORK

AGGREGATE TABLE



RAWSON MATERIALS
EXCLUSIVELY DISTRIBUTES
TO
ASTRO AGGREGATES



ASTRO
AGGREGATES

SIZES OF STONE AND GRAVEL

SIZES DESIGNATION (METRIC)	4" (100 mm)	3" (75 mm)	2 1/2" (63 mm)	2" (50 mm)	1 1/2" (37.5 mm)	1" (25 mm)	1/2" (12.5 mm)	1/4" (6.3 mm)	1/8" (3.2 mm)	No. 80 (180 um)	No. 200** (75 um)
Screenings*							100	90-100			0-1.0
1B								100	90-100	0-15	0-1.0
1A							100	90-100	0-15		0-1.0
1ST							100	0-15			0-1.0
1						100	90-100	0-15			0-1.0
2					100	90-100	0-15				0-1.0
3A				100	90-100	0-15					0-0.7
3			100	90-100	35-70	0-15					0-0.7
4A		100	90-100		0-20						0-0.7
4	100	90-100		0-15							0-0.7
5	90-100	0-15									0-0.7

* Screenings shall include all of the fine materials passing a 1/4 in. screen

** The minus No. 200 material requirements apply only to aggregates for the use in portland cement concrete, surface treatment, cold mix bituminous pavements and underdrain fiber material. The test (NYSDOT 201) will be performed on the entire sample of the designated size aggregate. Primary size does not apply in the determination of the minus No. 200 material.